



D&M Flooring
19168 Van Ness Ave
Torrance, CA 90501

Report Date:	9/10/2015
Project #:	Consumer
Report Of:	Finished Flooring Indicator 2
Report #:	D&M Flooring 7
Sample #:	2015-1169
Reporting Lab:	Benchmark Holdings, LLC 2710 West 5th Avenue, Eugene, OR 97402 USA Phone:541/484-9212 - Fax: 541/344-2735

Finished Flooring Indicator 2

ASTM D6007 Determining Formaldehyde Emissions Using Small Chamber

Chamber Results	
	Impinger
	#1
Observed Flow Rate (l/m):	1.000
Corr. Vol. of Air Sample:	30.503
Raw Absorbance Values:	0.010
	0.006
	0.006
Average Absorbance:	0.007
Unadjusted PPM:	0.015
Temp. Correction Factor 77°F:	1.02
R.H. Correction Factor 50% RH:	0.98
Standardized Concentration PPM:	0.015
Maximum PPM:	*

Production Data			
Product:	Tuscany		
Mill Code:	NS	Prod Date:	NS
Prod Group:	*	Control Date:	NS
Test Date:	8-Sep-15	Coll. Date:	NS

CHAMBER ID#:	4
Chamber Conditions	
Barometric Pressure (in):	30.40
Dry Bulb Temp (°F):	76.60
Relative Humidity (%):	51.10
Length of Test (minutes):	30.00

Comments: **Sample is engineered flooring with a hardwood plywood (HWPW) platform, tested as if it were HWPW-VC. Finished product is not regulated, however, sample emissions as tested were below published CARB standard for HWPW-VC (0.05 ppm).*

Parameters:			
Loading Ratio:	0.430	Volume =	.1191863m ³
Chamber Dimensions:	.49213m x .49213m x .49213m		
Air Exchange Rate:	0.50 ± 0.05 air changes per hour		

*The chamber is activated under positive pressure. The air sampling rate was 1.0 liters per minute at 30 ±2 minutes.
 *The samples were conditioned for seven days prior to testing at 70° to 80° F and 45% to 55% relative humidity. During conditioning, the formaldehyde background level was 0.01 parts per million or less.
 *Services performed for this project have been conducted with a level of care and skill ordinarily exercised by members of the profession currently practicing in this area under similar conditions and restraints. No warranty, expressed or implied, is made.
 *This report has been produced for the exclusive use of: D&M Flooring (client), and may not be reproduced except in its entirety, and only with the expressed, written approval of BMI. No one other than BMI's client shall be entitled to rely upon this report or the information contained herein. Any such unauthorized reliance on or use of this report will be at the third party's sole risk.



Respectfully Submitted,
 Benchmark Holdings LLC

 Travis R. Snapp
 Managing Director / COO
 Benchmark International LLC