



Reporting Laboratory:
Benchmark International, LLC (BMI)
2710 West 5th Avenue
Eugene, Oregon, USA 97402
Phone: +1 (541) 484-9212 / FAX: +1 (541) 344-2735

TESTING CONDUCTED ON BEHALF OF THE NAMED CLIENT BELOW:

D&M Flooring
19168 Van Ness Ave
Torrance, CA 90501
USA

REPORT INFORMATION:

Report Date: June 20, 2017
BMI Client/Project Number: 0721589
Report of: Finished Goods Ind #2 (Face/Back Exposed)
BMI Lab Report Number: 0721589-14
Sample ID Number(s): 2017-2008

ASTM D6007-02 Standard Test Method for Determining Formaldehyde Concentration in Air from Wood Products Using a Small Scale Chamber
NIOSH 3500: Formaldehyde by VIS (Chromotropic Acid procedure)
Standard Face-and-Back Sample Configuration

CHAMBER TEST CONDITIONS/PARAMETERS			
Product Type:	Finished Goods		
Chamber Load Ratio (m²/m³):	0.43		
Chamber Dimensions (m):	0.49 x 0.49 x 0.49 (Nominal)		
Chamber Volume (m³):	0.12m ³		
Air Exchange Rate:	0.5 +/- 0.05 air changes per hour		
Chamber Q/A Ratio (+/- 2%):	1.173		
No. Specimens in Charge:	1		
No. Faces Exposed:	2		
Barometric Pressure (in Hg):	29.7		
Temperature (°C):	Avg: 25.2	Min: 25.1	Max: 25.3
Relative Humidity (%):	Avg: 51	Min: 51	Max: 51
Length of Test (minutes):	30		

PRODUCT AND SAMPLE DATA			
Product Name/Description:	European Oak Engineered Flooring Sample ID: Silver Oak		
Panel Manufacturer:	Zhejiang Yuhua	Production Date:	12/18/2016
Supplier: <small>(if different than panel mfr)</small>	See Above	Sample Collection Date:	5/23/2017
Nominal Product Thickness:	1/2 in	Sample Test Date:	6/16/2017
Nominal Product Dimensions (L x W):	N/S N/S	Sample Wrapping Method:	Wrapped Together in Vapor Retarder
Face Surface Condition:	Stained/Coated	Back Surface Condition:	Unfinished
Lot/Batch No.:	20161218	Resin Type/Supplier:	N/S

TEST RESULTS	
	Impinger
Observed Air Flow Rate (Observed L/min):	1.00
Corrected Volume of Air Sample (Liters):	30.00
Raw Absorbance Values	
Absorbance #1	0.003
Absorbance #2	0.003
Absorbance #3	0.002
Average Absorbance:	0.003
Unadjusted Concentration (ppm):	0.01
Temperature Correction Factor 25°C:	0.98
Relative Humidity Correction Factor 50% R.H.:	0.98
Standardized Concentration (ppm):**	BLQ
**BLQ = Test result is below the limit of quantification (<0.015 ppm)	

TEST ANNOTATIONS
1) The test chamber is activated under positive pressure. The air sampling rate was 1.0 liters per minute (L/min) for 30 +/- 2 minutes.
2) The samples were conditioned for seven (7) days prior to testing. The sample conditioning environment was maintained at 75 +/- 5°F (24 +/- 3°C) and 50% +/- 5% relative humidity.
3) During conditioning and test, the background concentration of formaldehyde in air was 0.01 ppm or less.

OTHER COMMENTS
Not Applicable

This report has been produced for the exclusive use of: **D&M Flooring**
and may not be reproduced except in its entirety, and only with the express written permission of BMI. All test reports are subject to the current Benchmark Holdings, LLC Inspection and Test Report Publication Guidelines. Report users are responsible for contacting BMI to obtain a copy of current inspection and test report publication guidelines and/or to obtain written authorization to publish or reproduce this test report.

NOTE 1: Unless otherwise agreed in writing in advance by a duly authorized member of BMI management, test services are subject to the then-current Benchmark Holdings, LLC Standard Terms and Conditions of Service in effect at the time the test sample is submitted to the BMI laboratory. No one other than the named BMI Client above shall be entitled to rely upon this report or the information contained herein. Any such unauthorized reliance on or use of this report will be at the third party's sole risk.

NOTE 2: Services performed for this project have been conducted with a level of care and skill ordinarily exercised by members of the profession currently practicing in this area under similar conditions and constraints. No warranty, expressed or implied, is made.

Respectfully Submitted,

Laboratory Manager
Benchmark Holdings, LLC (BMH)
Benchmark International, LLC (BMI)

